

BOWSER-MORNER, INC.

Delivery Address: 4518 Taylorsville Road Dayton, Ohio 45424 Mailing Address: P.O. Box 51 Dayton, Ohio 45401
AASHTO/ISO 17025 Accredited

REPORT ON TESTS OF CONCRETE MASONRY UNITS

Report To: Tri-County Block & Brick, Inc.
Attn: Ed Kuhlman
1628 Airport Highway
Swanton, OH 43558

Report Date: 02/28/12
Job No.: 157263
Report No.: 707728
Submitted: 02/17/12

Specs: ASTM C 90

Test Method: ASTM C 140


Unit: 8" Normal Weight Loadbearing Concrete Masonry Unit - Hollow Core
8x4x16 Hollow Founders Brick Normal Weight

COMPRESSIVE STRENGTH					SPECIFICATIONS	
Specimen No.	6D	6E	6F	Average	Individual	Average
Length in Inches	15.53	15.53	15.52			
Width in Inches	7.65	7.63	7.64	7.64		
Height in Inches	3.70	3.69	3.69			
Equiv. Web Thickness, in/ft.	3.34	3.52	3.56	3.47		2 1/4 (2.25) Min.
Min. OW Thickness, in.	1.42	1.43	1.42	1.42		1 1/4 (1.25) Min.
Min. Web Thickness, in.	1.62	1.73	1.76	1.70		1 Min.
Gross Area, Sq. In.	118.8	118.5	118.6			
No. of Cells	2	2	2			
Total Load in lbs.	401,200	402,540	395,840			
Gross Unit Load, psi	3380	3400	3340	3370		
Gross Volume, Cu. Ft.	0.2544	0.2530	0.2532	0.2535		
Net Unit Load, psi	5920	5940	5840	5900	1700 Min.	1900 Min.
ABSORPTION					SPECIFICATIONS	
Specimen No.	6A	6B	6C	Average	Individual	Average
Wt. As Received, lbs.	20.20	20.30	20.20			
Suspended Wt., lbs.	11.70	11.80	11.75			
Wet Wt., lbs.	20.75	20.80	20.80			
Dry Wt., lbs.	19.90	20.00	19.95			
Absorption, lbs./Cu.Ft.	5.9	5.5	5.9	5.8	15 Max.	13 Max.
Absorption, % of Dry Wt.	4.3	4.0	4.3	4.2		
% Moisture, % Absorption	35.3	37.5	29.4			
Net Vol., Cu. Ft.	0.145	0.144	0.145	0.145		
Net Area, Sq. In.	67.7	67.5	67.9	67.7		
Dry Den, lbs./Cu.Ft.	137.2	138.7	137.6	137.8		
FIRE RATING						
12.5% Limestone Screening, 12.5% #9 Limestone, 75% Limestone Manufactured Sand						
Percent Solids:	57.1	%	Ohio Building Code (OBC) Table 721.3.2			
Equivalent Thickness:	4.4	inches	Fire Resistance Rating:	2 3/4 hr. (2.7 hr.)		
LINEAR SHRINKAGE						
Linear Shrinkage @ Equilibrium, %: Testing Not Requested - a complete ASTM C90 specification requires linear shrinkage						

Should you have any questions, or if we may be of further service, please contact me at (937) 236-8805, ext. 235.

JWF/bk/lbg
707728

1-File
1-ed@tricityblock.com


James W. Fletcher, Vice President
Director of Laboratory Services
Construction Services Division
CMTT# 0112

All Reports Remain The Confidential Property Of BOWSER-MORNER And No Publication Or Distribution Of Reports May Be Made Without Our Express Written Consent, Except As Authorized By Contract. Results Contained In This Report Are Reflective Only Of The Items Calibrated Or Tested. Unless Otherwise Agreed, Samples or Specimens Will Be Discarded Or Returned At Bowser-Morner's Discretion. AASHTO/ISO 17025 Accreditation applies only to the parameters included in BOWSER-MORNER'S current scope of accreditation. Go to www.bowser-morner.com/accreditations for review.